

ADCOR[®] 550 T-MI

Double protection system for construction joints using 2-in-1 pre-applied, post injectable hydrophilic waterstop for saline and brackish water ground condition

Product Description

Adcor[®]550 T-MI is a combined active and passive waterstop system with built in redundancy for the secure sealing of concrete construction joints subject to hydrostatic pressure. It comprises an outer hydrophilic sleeve activated in contact with water (active) for sealing the joint, and a reinforced injection tube for remedial treatment by resin injection (passive).

With the speed and simplicity of a single installation Adcor 550 T-MI provides the advantages of both a pre-applied barrier and a post injected waterstop system:

1. The outer hydrophilic sleeve gives the first protection level, it has been designed to swell with saline and brackish water ground condition,
2. The reinforced injection tube for remedial treatment by fast one component resin injection gives the reassurance of a second protection level.

Unlike standard injection systems that require resin injection in every case to be effective, Adcor 550 T-MI has built in waterstop protection from the special hydrophilic element, and only needs injection in extreme cases of leakage.

Advantages

Hydrophilic waterstop

- Volumetric expansion over 140% in 8% saline water
- Easy installation
- Non-polluting to ground water
- Retains cohesive strength at both original and expanded volume
- No need for protective steel mesh
- Conformable – can be installed onto a variety of irregular substrates
- Reinforced inner tube prevents damage to resin path
- Resists at least 5 bar (50 m) hydrostatic pressure.

Injection System


- Complete contact of the outer sleeve with the concrete
- Simple overlap jointing on site. Can be easily jointed to PVC Waterstops at movement joints
- Low pressure injection system therefore no need for electrical injection equipment
- Injection socket inlets can be installed and easily accessed
- Mechanical hand pump available for injection
- Minimal interruption to occupancy should the need for injection arise.

Adcor 550 T-MI hydrophilic injection hose has advantages over other waterstop systems with:

- A hydrophilic outer sleeve which expands on contact with water and seals small cracks and voids in the construction joints
- A filtration membrane outside the reinforced inner tube which prevents siltation of the injection hose and swelling of the external membrane.
- A steel wire reinforced inner tube which maintains its shape and does not collapse even under the extremes of external pressure.

Applications

- Construction joints for in-situ concrete structures
- Casting new concrete against existing concrete
- Floor slabs cast against diaphragm retaining walls, steel sheet piles and secant piled walls
- Joints between floor slabs and pile caps
- Remedial 'breaking out' of concrete.



Details shown are typical illustrations only and not working drawings. For assistance with working drawings and additional technical advice please contact GCP Applied Technologies Technical Services.

SUPPLY

| | |
|----------------------|---------------------|
| Adcor 550 T-MI KIT | Weight 14.4 kg |
| Each Box Contains: | |
| Adcor 550 T-MI | 8 x 5 m rolls (40m) |
| Reinforced PVC tube* | 4 metres + 16 caps* |
| Blue Trumpets* | 16 pieces |

| | |
|------------------------|---|
| Adcor 550MI clips* | 175 pieces |
| PVC tube clips | 16 pieces |
| Accessories | |
| Adcor 550MI Twinbox | 5 Units |
| Adcor 550MI Formholder | 50 Units |
| Adcor Mastic | 310 ml cartridge (12 per box) |
| Injection Material** | HA Flex LV AF resin & HA Flex Cat AF catalyst |

* can also be ordered separately

** for more detail refer to separate technical datasheet

PHYSICAL PROPERTIES

| Property of the Outer Skin | Typical Results |
|---|---------------------------------|
| Volumetric expansion in 8% saline water | >140% |
| Density | Approx. 1.46 kg/dm ³ |
| Expansion pressure under complete enclosure | > 0.70 N/mm ² |
| Resistance against Hydrostatic Pressure | up to 5 bar (50 m) |
| Installation temperatures | -15°C to 60°C |
| Minimum concrete cover | 70 mm |
| Property of the injection tube | |
| Consumption during injection | Minimum 190g/m to fill tube |
| Steel wire tensile strength | Approx. 1800 N/mm ² |

All test results shown in this data sheet are determined under laboratory conditions and with the product sample taken directly from stock in its original packing without any alteration or modification of its component parts.

Installation

- Adcor 550 T-MI should be installed on a smooth and dust-free surface free of loose material and laitance
- Keep Adcor 550 T MI dry prior to pouring concrete.
- Adcor 550 T-MI must be in direct contact with the construction joint substrate over its full length.
- The hoses are positioned between the reinforcement during second phase construction.
- Note the Adcor 550MI Twinbox or Formholder positions and connected inlet and outlets for location and access after concreting.
- Detailed installation instructions are available from the local GCP Representative.

Dimensions

Outer diameter of Adcor 550 T-MI: approx. 16 mm

Diameter of the spiral: approx. 8 mm

Thickness of hydrophilic skin: approx. 4 mm

Consumption

Quantities are dependent on the lengths of the construction joints and quantity of over laps. The consumption of injectable resin is dependent on the frequency and size of hollow voids around the Adcor 550 T-MI.

Storage

Adcor 550 T-MI should be stored under cover, clear of the ground. Protect the materials from all sources of moisture and frost. Shelf life is unlimited if correctly stored.

Accessories

Adcor Mastic

- Mastic for levelling the surface
- Packaging: 310 ml cartridge (12 per box)

To be ordered separately.

Health and Safety

Read the product label and Material Safety Data Sheets before use. Users must comply with all risk and safety phrases. For health and Safety questions on this product please contact GCP Applied Technologies.

gcpat.ae | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADCOR is trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA

Emirates Chemicals LLC, Festival Tower, P. O. Box 5006, Festival City, Dubai, United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.ae. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2021-02-05

gcpat.ae/solutions/products/joint-protection/ador-550-t-mi