

# DE NEEF<sup>®</sup> HA SOIL AF

Next generation, non-phthalate, one-component, high performance, low viscosity, hydrophobic, hydro-active, rigid polyurethane injection grout used to increase the load bearing capacity of loose soil

---

## Product Description

In its uncured form, HA SOIL AF is a dark brown, non-flammable, low viscous liquid without phthalate plasticisers. When HA SOIL AF comes into contact with water, the grout expands and quickly (depending on temperature and the amount of HA SOIL CAT AF catalyst used) cures to a rigid polyurethane foam.

## Field of Application

- High strength soil stabilisation.
- High strength anchoring in wet or dry conditions.
- Pre-injections for waterproofing and consolidation in front of TBM, drill-and-Blast and NATM.
- Combi-Grouting in combination with cement or micro-fine cements.
- Tie-back and screw rod anchoring in wet or dry conditions.
- Curtain injections and chemical containment.
- Soil stabilisation around sewer lines.
- Filling large voids in rock fissures, crushed faults, gravel layers in wet or dry conditions using special techniques and/or filled resins.

For additional information on areas of doubt, please consult your local GCP representative.

## Product Advantages

- ADR free transport.
- Next generation resin with improved performance.
- Improved cell structure of the cured compound resulting in better mechanical properties and durability.
- Non-phthalate resins, REACH compliant.
- Improved performance at temperatures below 5 °C, no crystallisation of HA SOIL™ Cat AF.
- Can be injected into silty sand with a coefficient of 10-6 m/s (or 15% of the particle size 0.074mm).
- Non-flammable, non-solvent.
- User friendly: one-component product.
- Controllable reaction times: by using catalyst curing times can be reduced.
- Cured compound is resistant to most organic solvents, mild acids, alkalis and micro-organisms (\*).

(\*) For chemical resistances please contact your GCP representative.

## Application

HA Soil AF is used for stabilising loose soils or to increase the load bearing capacity of these soils.

## 1. Soil investigation

- To determine the suitability of the soil to be grouted, the soil is to be in accordance with local guidelines and regulations. A full study of the situation and the characteristics of the soil has to be made prior to commencing the injections.

## 2. General considerations

- It is recommended that the soil injection is carried out at the lowest possible pressure. The required pressure is influenced by the load pressure on the soil, permeability, injection speed, resin characteristics, etc.
- The flow rate required for a successful injection needs to be determined by trial injection on the site prior to the actual work.
- Spacing and depth of the injection points will be determined after studying the soil and application requirements.

## 3. Preliminary checks

Before installing the injection tubes into the soil, check the following:

- Investigate the presence of municipal underground utilities such as water or power supply, sewers, underground water pockets, etc.
- Investigate the presence and behaviour of the ground water.
- Investigate the characteristics of the soil and the geological composition of the site.
- Test the permeability of the soil for water and resin.

## 4. Resin preparation

- Shake HA SOIL Cat AF well before use.
- Mix the resin with the predetermined amount of HA SOIL Cat AF catalyst using a slow speed mixer (400 to 600rpm). Shield the vessel with the premixed resin from water ingress since this will cause a reaction in the vessel and pumping equipment.

## 5. Injection

- The injection procedure can be split up in 4 steps.
- Installing the injection tube (sleeve port pipe/strainer pipe) to the planned depth.
- Start the injection with the mixed material.
- Controlled withdrawal of the injection tube at predetermined depths and time intervals.

## 6. Cleaning

- When the injection is finished, clean all tools and equipment, which have been in contact with the resin with DE NEEF® Washing Agent Eco. This should be done within 30 minutes. Do not use solvents or other cleaning products since they give less positive results and can create hazardous situations.
- Products should be disposed off according to local legislation.
- For further information concerning soil injections with HA SOIL AF, contact your local GCP representative.

## 7. Reactivity

REACTIVITY	% HA SOIL CAT AF	START REACTION	END REACTION	FOAM FACTOR
At 5 °C	0.5	Approx. 4'00"	Approx. 14'30"	Approx. 1V
	1.0	Approx. 2'10"	Approx. 6'30"	Approx. 2V
	1.5	Approx. 1'50"	Approx. 5'00"	Approx. 3V
	2.0	Approx. 1'20"	Approx. 4'10"	Approx. 3V
	2.5	Approx. 1'00"	Approx. 2'45"	Approx. 3V
At 10 °C	0.5	Approx. 3'50"	Approx. 12'05"	Approx. 1V
	1.0	Approx. 2'00"	Approx. 5'30"	Approx. 2V
	1.5	Approx. 1'40"	Approx. 4'30"	Approx. 3V
	2.0	Approx. 1'10"	Approx. 3'40"	Approx. 3V
	2.5	Approx. 55"	Approx. 2'40"	Approx. 3V
At 15 °C	0.5	Approx. 3'40"	Approx. 11'30"	Approx. 1V
	1.0	Approx. 1'50"	Approx. 5'00"	Approx. 2V
	1.5	Approx. 1'30"	Approx. 4'00"	Approx. 3V
	2.0	Approx. 1'05"	Approx. 3'10"	Approx. 3V
	2.5	Approx. 50"	Approx. 2'30"	Approx. 3V
At 20 °C	0.5	Approx. 3'30"	Approx. 10'50"	Approx. 1V
	1.0	Approx. 1'40"	Approx. 4'50"	Approx. 2V
	1.5	Approx. 1'20"	Approx. 3'50"	Approx. 3V
	2.0	Approx. 1'00"	Approx. 2'50"	Approx. 3V
	2.5	Approx. 45"	Approx. 2'20"	Approx. 3V
At 25 °C	0.5	Approx. 2'30"	Approx. 8'45"	Approx. 3V
	1.0	Approx. 1'20"	Approx. 4'30"	Approx. 3V
	1.5	Approx. 1'00"	Approx. 3'25"	Approx. 3V
	2.0	Approx. 45"	Approx. 2'30"	Approx. 3V
	2.5	Approx. 37"	Approx. 2'05"	Approx. 3V
At 30 °C	0.5	Approx. 2'20"	Approx. 8'00"	Approx. 3V
	1.0	Approx. 1'15"	Approx. 4'20"	Approx. 3V
	1.5	Approx. 55"	Approx. 3'05"	Approx. 3V
	2.0	Approx. 42"	Approx. 2'20"	Approx. 3V
	2.5	Approx. 34"	Approx. 2'00"	Approx. 3V
At 35 °C	0.5	Approx. 2'5"	Approx. 7'35"	Approx. 3V
	1.0	Approx. 1'10"	Approx. 3'50"	Approx. 3V
	1.5	Approx. 50"	Approx. 3'05"	Approx. 3V
	2.0	Approx. 38"	Approx. 2'10"	Approx. 3V
	2.5	Approx. 30"	Approx. 1'55"	Approx. 3V

## Technical Data/Properties

PROPERTY	VALUE	NORM
<b>HA SOIL AF</b>		
Uncured		
Solids	100%	EN ISO 3251
Viscosity at 25 °C (mPas)	Approx. 50	EN ISO 3219
Density (kg / dm <sup>3</sup> )	Approx. 1.115	EN ISO 2811
Flash Point ( °C)	140	EN ISO 2719
<b>HA SOIL CAT AF</b>		
Viscosity at 25 °C (mPas)	Approx. 15	EN ISO 3219
Density (kg / dm <sup>3</sup> )	Approx. 0.944	EN ISO 2811
Flash Point ( °C)	105	EN ISO 2719
<b>Cured</b>		
Density (kg / dm <sup>3</sup> )	Approx. 1.000	EN ISO 1183
Compressive strength (MPa)*	Approx. 12.5	EN 12190
Flexural strength (MPa)*	Approx. 2	EN 12190

## Appearance

HA SOIL AF: Dark brown liquid

HA SOIL CAT AF: Transparent liquid

## Consumption

Must be estimated by the engineer or operator and depends on type of work, soil porosity and volume of strengthened soil.

## Packaging

### HA SOIL AF

200kg or 25kg metal drum

1 pallet

24 x 25kg drums

4 x 200kg drums

## HA SOIL CAT AF

0.5L plastic bottle or 20 kg metal drum

1 pallet

84 boxes (1 box = 8 x 0.5L bottles)

24 x 20kg drum

## Storage

HA SOIL AF is sensitive to moisture and should be stored in original containers in a dry area. Storage temperature must be between 5 °C and 30 °C. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible.

Shelf life: 2 years.

## Health and Safety

Users must read and understand the product label and safety data sheet (SDS) for each system component before use. All users should acquaint themselves with this information prior to working with the material. Carefully read detailed precaution statements on the product label and SDSs before use. The most current SDSs can be obtained from the GCP website at [gcpat.com](http://gcpat.com) or by contacting GCP at +1-703-741-5970.

[gcpat.ae](http://gcpat.ae) | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Cut is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2019 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.ae](http://www.gcpat.ae). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15

[gcpat.ae/solutions/products/de-need-waterproofing-injection-solutions/de-need-ha-soil-af](http://gcpat.ae/solutions/products/de-need-waterproofing-injection-solutions/de-need-ha-soil-af)