

# PREPRUFE® Grout CEM 100

Cementitious, non shrink grout for re-profiling of pile heads.

## **Product Description**

PREPRUFE <sup>®</sup>Grout CEM 100 is a high strength, cementitious, non shrink grout for re-profiling of pile heads prior to the application of PREPRUFE <sup>®</sup>Grout EG 75. When used with PREPRUFE <sup>®</sup>Grout EG 75, continuity of PREPRUFE <sup>®</sup> waterproofing systems at pile heads and similar structural penetrations is achieved. PREPRUFE <sup>®</sup>Grout CEM 100 contains cements, graded mineral aggregates and polymers which are pre-blended in a 25 Kg bag.

Measured addition of the recommended amount of clean water produces a free flowing, high strength, non shrink grout.

## **Product Advantages**

- compatible with PREPRUFE® Grout EG 75
- low permeability
- shrinkage compensated (non shrink)
- high bond to concrete substrates
- rapid strength gain
- high compressive and flexural strengths
- flowable consistency
- chloride free
- easy mixing and placing

## System Components

To achieve continuity of PREPRUFE®sheet waterproofing systems at pile heads and similar structural penetrations, you will need the following system components.

- PREPRUFE® Grout EG 75 impermeable epoxy grout forwaterproofing of pile heads (see separate product data sheet)
- BITUTHENE® LM high performance, liquid membrane
- PREPRUFE® 300R sheet membrane
- PREPRUFE® Tape for sealing of laps in PREPRUFE® sheet membranes
- ADCOR® 500S hydro-expansive waterstop for concrete construction joints

# **Applications**

- recommended thickness range 10 mm to 100 mm
- re-profiling of pile heads before the application of PREPRUFE® Grout EG 75
- re-profiling of structural penetrations through PREPRUFE® sheet waterproofing systems before the application of PREPRUFE® Grout EG 75



## **Product Application**

#### Surface Preparation:

Concrete substrates should be free from laitance, surface contaminants and curing compounds. Remove any friable material and laitance by mechanical means. Remove rust from any reinforcement that will be encapsulated by the cementitious grout. Adhesion to smooth substrates can be improved by using DARAWELD® BA3 acrylic bonding agent (see separate product data sheet). Saw cut where necessary to avoid feather edges. Continuously pre-soak the substrate with clean water for at least an hour before grout application, this ensures substrate saturation. Remove any ponded water immediately before grout application, manually or with an air lance.

#### Formwork:

Formwork must be constructed to be leak-proof as PREPRUFE®Grout CEM 100 is fluid when mixed. Seal all joints in formwork with a cartridge of sealant/adhesive. All formwork should be coated with a mineral oil or water based release agent, before the grout is placed.

#### Mixing and Placing:

Measure 3.50 to 3.75 litres of clean water into a clean 20 litre pail, slowly add the full 25 Kg grout contents from the bag, whilst mixing continuously with a clean paddle mixer and slow speed drill (max 400 rpm). Scrape in any unmixed material from the side and bottom of pail with a trowel. Mix for a minimum of five minutes or until a fluid homogenous consistency is achieved. For large volume grout mixes, use a high shear vane mixer or similar. Pour the grout from the pail into the forms continuously, if more than 13 litres of grout is required, mix the next unit whilst the first is being poured to enable continuous placement. At ambient temperatures of more than 35°C, store products in the shade and use chilled water for mixing. This will maximize working time when mixed.

#### Surface Preparation Whilst Plastic

To maximise interface adhesion between PREPRUFE®Grout CEM 100 and PREPRUFE®Grout EG 75, the upper surface of PREPRUFE®Grout CEM 100 should be scored with a notched trowel, while the material is in its plastic state. Alternatively, wait until the cementitious grout has hardened and prepare the surface by sand blasting or a similar mechanical method.

#### Cleaning:

Clean mixers and trowels with water.

# Supply, Estimating and Storage

SUPPLY	25 KG PAPER BAGS
Water addition for flowable consistency	3.50 – 3.75 Lts/25 kg
Water addition for mortar consistency	3.50 – 3.75 Lts/25 kg
Yield at flowable consistency	13 Lts/25 Kg



Store unopened in original packaging in cool dry conditions.

Shelf life in these conditions is 12 months from date of manufacture.

#### **Technical Data**

PREPRUFE® GROUT CEM 100	TYPICAL VALUE	TEST METHOD
Thickness range	10 mm –100 mm	
Fresh wet density at fluid consistency	2.20 Kg/Lit	EN 12350-6
Working time at 25°C	20 mins	
Compressive strength 7 day at 23°C	60 N/mm <sup>2</sup>	ASTM C 109
Compressive strength 28 day at 23°C	75 N/mm²	ASTM C 109
Flexural strength 28 day at 23°C	10 N/mm <sup>2</sup>	BS 6319 : Part 3
Bond strength to concrete 28 day at 23°C	1.5 N/mm <sup>2</sup>	ASTM D 4541
Water penetration	< 10 mm	BS 12390-8

**Note**: All test results shown in this data sheet are determined under laboratory conditions, using product samples taken from inventory in original packaging, without alteration or modification.

# Health and Safety

Before using this product, read the product labels and comply with all health and safety advice. Further health and safety information is available from the products Safety Data Sheet (SDS) available from GCP or on line at gcpat.com.

### gcpat.ae | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

PREPRUFE is a trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.ae. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15