

# DARAGROUT<sup>®</sup> 191 (EH)

Non-shrink grout admixture for use with injection grouts requiring controlled expansion and high flowability Additive for non-shrink grout acc. to EN 934-4:T2

## Fields of Application

DARAGROUT<sup>®</sup>191 (EH) is a grout admixture for injection grouts in prestressed concrete. Grout admixtures compensate the plastic shrinkage and the settlement of the cementitious grout, in the ducts containing the steel tendons and secure an effective bond between the tendons and the posttensioned concrete structural members. Therefore, the protection against corrosion of the prestressed elements is secured.

Further fields of application include the manufacture of highly flowable cement grout for injection into voids and for a complete filling, e.g. in underground cavity and tunnel constructions, brickwork constructions, improving properties of the ground by consolidating via injections, as e.g. underpinning of foundations, water sealing of dam projects (grout curtain), large field injections for waterproofing and compaction of the substrate of tunnels.

## Technical Data

DARACEM 19CFU	
Effective Component	aluminium powder
Form	powder
Homogeneity	homogeneous (tested acc. to DIN V 20000-101, annex A)
Colour	light brown
Dry material content	95,0 ± 5,0 M.-%
pH-value	9.3 ± 1 (3% suspension)
Total chloride content	< 0.10 m.-%
Water-soluble chloride content	< 0.10 m.-%
Alkali content	< 10.0 m.-%
Storage	Keep dry and well closed in original containers
Recommended Dosage	0.20–2.00 m.-% of cement
Delivery Form	25 kg sacks; 25 kg boxes (50 bags with 500 g)
Physiological effect	May irritate skin and eyes; see SDS
Shelf-life	approx. 2 year in closed original containers

## Properties/Mode of Action

DARAGROUT 191 (EH) enables a significant reduction in the water demand and in bleeding as well as a considerable increase of flowability, even at higher temperatures and controlled swelling properties to compensate the natural settlement of the cement paste.

## Dosage and Use

DARAGROUT 191 (EH) is pre-dosed into the gauging water, subsequently the cement is slowly added. Mixing should be finished after 4 minutes at the latest. To prevent segregation of the grout, it must be constantly mixed in the storage container.

## Special Information

Suitable for use with injection grouts in prestressed concrete. When using non-shrink grout admixtures with chromate-reduced cements, there may be unexpected side-effects, e.g. changed course of setting or hardening.

**Preliminary tests according to official national standards are always required before use!**

**gcpat.ae | United Arab Emirates customer service: +971 4 5139560**

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DARAGROUT is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

Pyrrmonter Straße 56, 32676 Lügde

GCP0082-1216 DARAGROUT-191-EH\_DE-EN

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.ae](http://www.gcpat.ae). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-18

[gcpat.ae/solutions/products/daragROUT-191-eh](http://gcpat.ae/solutions/products/daragROUT-191-eh)