

DAREX[®] AE3

Air Entraining Agent

Product Description

DAREX[®]AE3 is a liquid airentraining agent for use in the production of air entrained concretes, blocks and cementitious compositions. DAREX[®]AE3 is formulated from carefully selected raw materials and is manufactured under controlled conditions. It is based on the salt of an ether sulphate and conforms to EN934-2, ASTM designation C260 and complies with BS 5075: Part 2, for air-entraining admixtures.

Product Advantages

- Improves resistance to freeze/thaw conditions.
- Resistance to the disruptive action of de-icing salts and other liquids is improved.
- Cohesion of mixtures liable to segregation is improved.
- Bleeding of excessive mixing water is reduced.
- Entrained air is not readily lost from plastic concrete mixtures on standing and prolonged mixing does not normally cause excessive over- entrainment of air.
- DAREX[®] AE3 is particularly suitable for use in conjunction with concretes containig sands into which it is difficult to entain air

Typical Properties

APPEARANCE	AMBER LIQUID
Air Entrainment:	See "Addition Rates"
Chloride Content:	nil as per EN480-10
Freezing Point:	-2 °C

Addition Rates

Range: 30 ml - 180 ml per 100 kg cement. The amount of DAREX[®]AE3 required is dependent on the characteristics of the concrete or mortar mixtures concerned, together with the degree of air entrainment required. Factors which can affect this are:

- Nature and grading of the aggregates, particularly fine aggregates.
- Cement content and type of cement used.
- Water/cement ratio.
- Workability of the mixture.
- Temperature.
- Type and efficiency of mixing equipment.
- Normal good site control gives excellent consistency of results.

It is essential that the final assessment of the dosage should be made after the site trials. As a guide to these trials, an addition rate of 60 ml - 180 ml DAREX[®]AE3 per 100 kg cement is recommended (where DAREX[®]AE3 is used in concretes containing pulverised fuel ash, the dosage rate may typically be twice the range quoted above). For semi-dry mixtures 280 ml - 400 ml DAREX[®]AE3 per 100 kg cement is recommended.

For advice and assistance with your trials we would recommend that you consult GCP Applied Technologies.

DAREX[®]AE3 is supplied ready for use. It should be added to concrete or mortar mixtures during the mixing process at the same time as the water or the aggregates.

Overdosing with DAREX[®]AE3 will normally produce an increase in air content and workability, but will have no effect on the setting time or early strength development.

Compatibility

With cements:

DAREX[®]AE3 can be used with all types of Ordinary Portland Cement, including Sulphate Resisting Cement. For use with special cements we recommend that you consult GCP.

With other admixtures:

DAREX[®]AE3 should not be premixed with other admixtures. The performance of the material may be affected by the presence of other chemicals and we recommend that GCP be consulted in such circumstances.

Dispensing

It is preferable that liquid admixtures for concrete should be introduced into the mixer by means of automatic dispensing equipment. A range of equipment is available, and advice on supply and fitting is available from GCP on request.

Packaging

DAREX[®]AE3 is supplied in 250 litre, non-returnable containers. Alternatively, bulk deliveries can be arranged.

Storage

DAREX[®]AE3 should be stored above 0 °C and protected from frost. If the product does freeze, it should be carefully thawed before mixing.

Storage life in manufacturer's drums:

12 months from the date of manufacture.

Storage life bulk storage:

12 months from the date of delivery.

Health and Safety

See DAREX[®]AE3 Safety Data Sheet or consult GCP.

Technical Service

The Technical Service department of GCP is available to assist you in the correct use of our products.

gcpat.ae | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Darex is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

830-832 Fountains Court Birchwood Boulevard, Birchwood Warrington Cheshire WA3 7QZ.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.ae. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-18

gcpat.ae/solutions/products/darex-ae3