

DBM® P

Plasticiser for Semi-Dry Mixes

Product Description

DBM [®]P is a liquid air entraining plasticiser used in semi-dry concrete mixes to improve the cohesiveness and compressive strength of concrete blocks and bricks. These effects are achieved by the combination of the powerful deflocculating and plasticising action of DBM [®]P.

DBM [®]P is formulated from a carefully selected blend of synthetic and naturally derived raw materials to give a consistent product.

Advantages

- Improves cohesiveness and compressive strength.
- DBM® P allows cement savings of approximately 10% without loss in strength.
- Increase durability, reduced permeability.
- Effective in both air cured and steam cured conditions.
- DBM® P is effective in all types of block and brick machines, reducing mould box wear.

Typical Properties

DBM® P	
Appearance	dark brown liquid
Specific Gravity	1.09 at 20 °C
Chloride Content	Nil

Method of Use

DBM [®]P is supplied ready for use. It should be added to concrete mixes during the mixing process at the same time as the water. It should not be added directly to the cement. No extension of normal mixing time is necessary.

Dispensing

It is preferable that liquid admixtures for concrete should be introduced into the mixer by means of automatic dispensing equipment. Details are available upon request.

Health and Safety

For further information see DBM®P SDS (Safety Data Sheet) or consult GCP



Packaging

DBM [®]P is supplied in nominal 210 litre free, non returnable containers.

Alternatively, 1000 litre IBCs or bulk deliveries can be arranged.

Storage

DBM [®]P should be stored in original containers or suitable closed tanks, preferably out of direct sunlight and protected from extremes of temperature.

Storage Life in Manufacturer's Drums:

12 months from the date of manufacture

Storage Life in Bulk Storage:

12 months from the date of delivery

Compatibility with Cements

DBM [®]P can be used with all types of Portland cement including cement replacement materials.

Compatibility with other Admixtures

DBM [®]P should not be premixed under any circumstances with other admixtures. While some admixtures can be usefully combined within the same mix the performance of this product may well be affected by the presence of other chemicals and we recommend that GCP Applied Technologies be contacted for advice in all such circumstances.

Addition Rates

Range: 0.2%-0.4% volume by weight of cement

The performance of DBM[®]P is best assessed after preliminary tests to determine the optimum dosage level and effect on the properties of the concrete.

As a guide to these trials an addition rate of 200 ml-400 ml DBM $^{\$}$ P per 100 kg cement is recommend.

Effects of Overdosing

Serious overdosing of DBM[®]P will generally produce an increase in workability and cohesion of the mix. This may be accompanied by retardation of the setting characteristics of the concrete. However, provided the concrete is properly cured, the ultimate strength will generally be higher than that of normal concrete.



Technical Service

The Technical Service Department of GCP is available to assist you in the correct and best use of our products. These resources and advice are at your disposal entirely without obligation. Please contact:

GCP

Emirates Chemicals LLC
Festival Tower, Suite 1701
Dubai Festival City
P.O. Box 5006
Dubai, United Arab Emirates

Tel: +971 4 2329901 Fax: +971 4 2329940 Email: meinfo@grace.com

gcpat.ae | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DBM is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.ae. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.