

WRDA[®] 30

Concrete Plasticiser

Product Description

WRDA[®]30 is a high efficiency plasticiser which substantially improves early and ultimate strengths of concrete by effective water reductions. WRDA[®]30 is ideal for use in the design of high performance concretes for ready mixed concrete operations. It can also be used to impart high workability to concrete mixtures and to extend transit and placement times.

WRDA[®]30 is formulated from specially selected polymer systems which have been carefully matched to optimise the synergy between dispersing properties and improvement of cement hydration. WRDA[®]30 conforms to EN934-2, Type A and Type D of ASTM C 494 and with BS 5075: Part 1.

Benefits and Advantages

- Substantial increases in workability
- Improves early and ultimate strengths
- Low alkali content
- Low dosage capability
- Excellent performance in mixtures containing cement replacements
- Improves cement economies
- Excellent workability retention properties

Typical Properties

Appearance	Dark Brown liquid
Air Entrainment:	nil
Chloride Content:	nil, as per EN480-10
Freezing Point:	-3 °C

Addition Rates

Range: 200 ml – 500 ml per 100 kg cement (0.2% – 0.5%) volume by weight cement.

WRDA[®]30 is a versatile, high performance product that can benefit a wide variety of applications. As with most products of this type, the level of effect of WRDA[®]30 is governed, within limits, by the quantity of products used and the specific nature of the concrete mixture.

The performance of WRDA®30 is best assessed after preliminary tests using the actual concrete materials to determine the optimum dosage and effect on both plastic and hardened concrete properties. As a guide to these trials, we recommend an addition rate of 300ml per 100kg cement as a starting point.

WRDA®30 is supplied ready for use. It should be added to the concrete mix during the mixing cycle with the water, after the addition of the cementitious component. It should not be added directly to the cement. Overdosing of WRDA®30 will generally increase set retardation which is governed by the level of addition. Retardation will be exaggerated in low temperatures and when Sulphate Resisting Cement or cement replacements are used. Large overdoses will lead to considerable increases in workability. In cases of overdosing, care must be taken to ensure that the concrete is properly cured while in its plastic state.

Compatibility

With cements:

WRDA®30 can be used with all types of Portland Cement. It can also be used in concretes containing replacement materials such as ground granulated blast furnace slag and pulverised fuel ash. For use with other cements we recommend you consult GCP Applied Technologies.

With other admixtures:

WRDA®30 should not be pre-mixed with other admixtures.

The performance of the material may be affected by the presence of other chemicals. We recommend you consult GCP Applied Technologies in such circumstances.

Dispensing

Liquid admixtures should be introduced into the mixer by means of automatic dispensing equipment. A range of equipment and advice on supply and fitting are available from GCP Applied Technologies on request. WRDA®30 must not be allowed to come in contact with other admixtures prior to being mixed into the concrete.

Health and Safety

See WRDA®30 SDS (Safety Data Sheet) or consult GCP Applied Technologies.

Packaging

WRDA®30 is supplied in 205-litre, non-returnable containers. Alternatively, bulk deliveries can be arranged.

Storage

WRDA®30 should be stored above 0°C and protected from frost. If the product does freeze, it should be carefully thawed before mixing.

Storage life in manufacturer's drums:

12 months from date of manufacture

Storage life bulk storage:

12 months from date of delivery

Technical Service

The Technical Service department of GCP Applied Technologies is available to assist you in the correct use of our products.

gcpat.ae | United Arab Emirates customer service: +971 4 5139560

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

WRDA is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

830-832 Fountains Court Birchwood Boulevard, Birchwood Warrington Cheshire WA3 7QZ.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

P. O. Box 5006, Office 2104, 21 Floor, The Exchange Tower, Opp. JW Marriott Marquis Hotel, Business Bay, Dubai – United Arab Emirates

This document is only current as of the last updated date stated below and is valid only for use in the UAE. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.ae. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15

gcpat.ae/solutions/products/wrda-30